

P.S. FILM - EASYWEED®

SPECIFICATIONS

| Composition | Average Thickness | Carrier | Certifications |
|-------------|-------------------|--------------------|----------------|
| PU | 90 microns | Adhesive polyester | |

APPLICATION INSTRUCTIONS

| Applies on | SUGGESTED CUTTING SETTINGS | | | TRANSFER SETTINGS | | | |
|---|----------------------------|----------|-----------|-------------------|---------------|----------------------|----------|
| cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles) | Blade | Pressure | Speed | Time | Temperature | Pressure | Peel |
| | 45° | 60 gf | 30 cm/sec | 15 seconds | 150°C (302°F) | Medium (2,5/3,5 bar) | hot/cold |

- Cut the material mirrored
- Peel off excess material (Tip: use a heated surface for faster and easier "weeding")
- Place the decoration on the garment
- Apply following the recommended parameters
- Remove the carrier hot or cold

PRODUCT HIGHLIGHTS

- Wide range of colors
- Can be Layered
- Suitable for clothing for children and babies

NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

| Washing | Ironing | Tumble dry | Dry cleaning | Storage Shelf Life | Storage Temperature | Storage Conditions | Position |
|------------------------|----------------|--------------------|--------------|--------------------|-----------------------|-----------------------------|----------|
| Up to 80°C, inside-out | YES inside-out | YES (cotton cycle) | YES | Up to 2 years | Between 18°C and 26°C | Away from sunlight and dust | Vertical |

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management System
ISO 9001:2015
ISO 14001:2015
www.tuv.com
ID: 9105027958

